

IN THE CLAIMS:

1. to 25. (Canceled)

26. (Currently Amended) A cosmetic composition, comprising a cosmetically acceptable carrier containing:

(a) at least one fixing film-forming polymer ~~which that~~ is a branched block copolymer consisting essentially of, as principal monomers, (1) at least one monomer selected from the group consisting of C₁₋₂₀ alkyl acrylate, N-mono-(C₂₋₁₂) alkylacrylamide, N-mono-(C₂₋₁₂) alkylmethacrylamide, N,N-di-(C₂₋₁₂) alkylacrylamide and N, N-di-(C₂₋₁₂) alkylmethacrylamide, and (2) at least one monomer selected from the group consisting of acrylic acid, methacrylic acid, and acrylic and methacrylic acids, the polymer having a structure comprising hydrophobic blocks onto which more hydrophilic blocks are attached via bi-functional units,

(b) at least one thickening agent ~~which that~~ is a cross-linked or non-cross-linked homopolymer or copolymer based on acrylic acid or methacrylic acid or acrylic and methacrylic acid, and

(c) at least one co-thickening agent ~~which that~~ is a non-cellulosic thickening polymer different from thickening agent (b), wherein the fixing film-forming polymer ~~that~~ is a branched block copolymer consists essentially of n-butyl acrylate, acrylic acid, methacrylic acid, and allyl methacrylate ~~as a bifunctional monomer~~.

27. (Canceled)

28. (Previously Presented) The cosmetic composition according to claim 26, wherein the concentration of fixing film-forming polymer is between 0.1 and 10% by weight relative to the total weight of the composition.

29. (Previously Presented) The cosmetic composition according to claim 28, wherein the concentration of fixing film-forming polymer is between 1 and 5% by weight relative to the total weight of the composition.

30. (Previously Presented) The cosmetic composition according to claim 26, wherein the thickening agent (b) is a cross-linked acrylic acid homopolymer.

31. (Previously Presented) The cosmetic composition according to claim 26, wherein the thickening agent (b) is a copolymer of acrylic acid or methacrylic acid and a C₁₀₋₃₀ alkyl acrylate or methacrylate.

32. (Previously Presented) The cosmetic composition according to claim 26, wherein the concentration of thickening agent (b) is between 0.1 and 3% by weight relative to the total weight of the composition.

33. (Previously Presented) The cosmetic composition according to claim 32, wherein the concentration of thickening agent (b) is between 0.2 and 2% by weight relative to the total weight of the composition.

34. (Previously Presented) The cosmetic composition according to claim 26, wherein the co-thickening agent (c) is of natural origin.

35. (Previously Presented) The cosmetic composition according to claim 34, wherein the co-thickening agent (c) is guar gum, xanthan gum, scleroglucan gum, gelan gum, rhamsan gum, karaya gum, an alginate, maltodextrin, starch, or carob flour.

36. (Canceled).

37. (Previously Presented) The cosmetic composition according to claim 26, wherein the concentration of the co-thickening agent is between 0.05 and 2% by weight relative to the total weight of the composition.

38. (Previously Presented) The cosmetic composition according to claim 37, wherein the concentration of the co-thickening agent is between 0.1 and 1% by weight relative to the total weight of the composition.

39. (Currently Amended) A method for the styling and fixing of hair, comprising applying to the hair a cosmetic composition comprising a cosmetically acceptable carrier containing:

(a) at least one fixing film-forming polymer ~~which that~~ is a branched block copolymer consisting essentially of, as principal monomers, (1) at least one monomer selected from the group consisting of C₁₋₂₀ alkyl acrylate, N-mono-(C₂₋₁₂) alkylacrylamide, N-mono-(C₂₋₁₂) alkylmethacrylamide, N,N-di-(C₂₋₁₂) alkylacrylamide and N,N-di-(C₂₋₁₂) alkylmethacrylamide, and (2) at least one monomer selected from the group consisting of acrylic acid, methacrylic acid, and acrylic and methacrylic acids, the polymer having a structure comprising hydrophobic blocks onto which more hydrophilic blocks are attached via bi-functional units,

(b) at least one thickening agent ~~which that~~ is a homopolymer or copolymer based on acrylic acid or methacrylic acid or acrylic and methacrylic acid ~~which that~~ is cross-linked or non-cross-linked, and

(c) at least one co-thickening agent ~~which that~~ is a non-cellulosic thickening polymer different from thickening agent (b), wherein the composition has a viscosity of at least about 1.9 Pa.s.

40. (Canceled)

41. (Currently Amended) A cosmetic composition, comprising a cosmetically acceptable carrier containing:

- (a) at least one fixing film-forming polymer ~~which that~~ is a branched block copolymer consisting essentially of, as principal monomers, (1) at least one monomer selected from the group consisting of C₁₋₂₀ alkyl acrylate, N-mono-(C₂₋₁₂) alkylacrylamide, N-mono-(C₂₋₁₂) alkylmethacrylamide, N,N-di-(C₂₋₁₂) alkylacrylamide and N, N-di-(C₂₋₁₂) alkylmethacrylamide, and (2) at least one monomer selected from the group consisting of acrylic acid, methacrylic acid, and acrylic and methacrylic acids, the polymer having a structure comprising hydrophobic blocks onto which more hydrophilic blocks are attached via bi-functional units,
- (b) at least one thickening agent ~~which that~~ is a cross-linked or non-cross-linked homopolymer or copolymer based on acrylic acid or methacrylic acid or acrylic and methacrylic acid, and
- (c) at least one co-thickening agent ~~which that~~ is guar gum, wherein the composition has a viscosity of at least about 1.9 Pa.s.

42. (Currently Amended) The cosmetic composition according to claim 41, wherein:

- (a) said at least one fixing film-forming polymer is a branched block copolymer consisting essentially of, as principal monomers, n-butyl acrylate, acrylic acid, methacrylic acid, and allyl methacrylate ~~as a bifunctional monomer~~, and
- (b) said at least one thickening agent is a cross-linked homopolymer based on acrylic acid.

43. (Previously Presented) The cosmetic composition according to claim 42, wherein the concentration of fixing film-forming polymer is between 0.1 and 10% by weight relative to the total weight of the composition, the concentration of thickening agent (b) is between 0.1 and 3% by weight relative to the total weight of the composition, and the concentration of the co-thickening agent (c) is between 0.05 and 2% by weight relative to the total weight of the composition.

44. (Previously Presented) The cosmetic composition according to claim 42, wherein the concentration of fixing film-forming polymer is between 0.1 and 10% by weight relative to the

total weight of the composition, the concentration of thickening agent (b) is between 0.2 and 2% by weight relative to the total weight of the composition, and the concentration of the co-thickening agent (c) is between 0.1 and 1% by weight relative to the total weight of the composition.

45. (Currently Amended) The method for the styling and fixing of hair, comprising applying to the hair a cosmetic composition comprising a cosmetically acceptable carrier containing:

(a) at least one fixing film-forming polymer ~~which that~~ is a branched block copolymer consisting essentially of, as principal monomers, (1) at least one monomer selected from the group consisting of C₁₋₂₀ alkyl acrylate, N-mono-(C₂₋₁₂) alkylacrylamide, N-mono-(C₂₋₁₂) alkylmethacrylamide, N,N-di-(C₂₋₁₂) alkylacrylamide and N,N-di-(C₂₋₁₂) alkylmethacrylamide, and (2) at least one monomer selected from the group consisting of acrylic acid, methacrylic acid, and acrylic and methacrylic acids, the polymer having a structure comprising hydrophobic blocks onto which more hydrophilic blocks are attached via bi-functional units,

(b) at least one thickening agent ~~which that~~ is a homopolymer or copolymer based on acrylic acid or methacrylic acid or acrylic and methacrylic acid ~~which that~~ is cross-linked or non-cross-linked, and

(c) at least one co-thickening agent ~~which that~~ is guar gum, wherein the composition has a viscosity of at least about 1.9 Pa.s, wherein the fixing film-forming polymer ~~that~~ is a branched block copolymer consists essentially of n-butyl acrylate, acrylic acid, methacrylic acid, and allyl methacrylate ~~as a bifunctional monomer~~.

46. (Currently Amended) The method according to claim 45, wherein:

(a) ~~said at least one fixing film-forming polymer is a branched block copolymer consisting essentially of, as principal monomers, n-butyl acrylate, acrylic acid, methacrylic acid, and allyl methacrylate as a bifunctional monomer, and~~

(b) ~~said at least one thickening agent is a cross-linked homopolymer based on acrylic acid.~~

47. (Previously Presented) The method according to claim 46, wherein the concentration of fixing film-forming polymer is between 0.1 and 10% by weight relative to the total weight of the composition, the concentration of thickening agent (b) is between 0.1 and 3% by weight relative to the total weight of the composition, and the concentration of the co-thickening agent (c) is between 0.05 and 2% by weight relative to the total weight of the composition.

48. (Previously Presented) The method according to claim 46, wherein the concentration of fixing film-forming polymer is between 0.1 and 10% by weight relative to the total weight of the composition, the concentration of thickening agent (b) is between 0.2 and 2% by weight relative to the total weight of the composition, and the concentration of the co-thickening agent (c) is between 0.1 and 1% by weight relative to the total weight of the composition.